

## **MONOKOTE® Z-3306**

# Thermal Barriers Product data and application instructions

## **Product Description**

Monokote® Z-3306 Thermal Barrier is a cementitious fire protective coating specifically formulated for application over rigid, urethane and polystyrene foam plastics. Spray applied to interior foam surfaces on walls and ceilings, Z-3306 forms a hard, durable, monolithic thermal barrier against heat and fire.

Z-3306 is a mill-mixed product requiring only the addition of water. It can be easily applied to required thickness in a single pass resulting in an efficient, low cost method of meeting building code and insurance requirements.

In developing Z-3306, GCP Applied Technologies has utilized its experience and technology as the producer of Monokote spray applied fireproofing products—the most widely used structural steel fireproofing brand in North America. Sales and technical personnel located throughout the United States and Canada provide close technical support to contractors, owners and specifiers.

#### **Benefits**

While specific requirements differ from locality to locality, the use of foam plastics for most building occupancies is permitted only when they are protected by an approved thermal barrier. Z-3306 has been successfully fire-tested and listed by Underwriters Labora-tories Inc. and Factory Mutual. Z-3306 has a proven field and laboratory record of performance, reliability, ease of application and low in-place cost.

- **Proven fire test performance**—Z-3306 has successfully passed UL requirements as a thermal barrier over foam plastics.
- **Economical**—Ease of installation makes Z-3306 a low cost way to protect foam plastics.
- **Workable**—After being spray applied, Z-3306 may be lightly trowelled.
- **Damage resistant**—Z-3306 dries to a hard, durable surface which resists damage.

Testing Agency	Test Method	Substrate	Thickness of Z-3306	Test Result
Underwriters	UL 1715	Urethane foam	3⁄8 in. (10 mm)	Z-3306 approved
Laboratories Inc. (ULI)	(Room fire test)			
(USA)				
	(UBC 26-3)	Styrene foam	3/8 in. (10 mm)	Z-3306 approved
ULI (USA)	ASTM E119 Exposure	Urethane foam	¾ in. (19 mm)	15 minute rating
	(UBC 26-2)		1½ in. (29 mm)	30 minute rating
	CAN/ULC-S101*			
ULI (USA)	ASTM E84	Urethane foam	½ in. (13 mm)	Flame spread 10
	(Tunnel test)			Smoke developed 0
		Styrene foam	½ in. (13 mm)	Flame spread 5
				Smoke developed 0
ULC (Canada)	CAN4-S124M	Urethane foam	⅓ in. (21 mm)	Classification A
		Urethane foam	<sup>1</sup> / <sub>16</sub> in. (16 mm)	Classification B
		Urethane foam	<sup>13</sup> ⁄ <sub>16</sub> in. (20 mm)	Classification C
		Urethane foam	<sup>1</sup> / <sub>16</sub> in. (16 mm)	Classification D
Factory Mutual System®	FM 4975	Urethane foam	⅓ in. (21 mm)	Delay ignition
				10–15 minutes
		Styrene foam	11/8 in. (29 mm)	Delay ignition
				10–15 minutes

<sup>\*</sup>Test results are based on ASTM E119 testing. CAN/ULC-S101 is equivalent to ASTM E119.

- **Humidity resistant**—Z-3306 can be used in high humidity conditions and reduces sweating often experienced in vegetable storage areas.
- **Washable**—When trowelled and painted, Z-3306 can be washed and cleaned.

### **Physical Properties**

- Bond strength—500 lbs/ft<sup>2</sup>
- Color—Grey or off-white
- **Theoretical yield**—25 bd ft/bag (50 ft² at ½ in. thickness)

#### Installation

Z-3306 is packaged in poly-lined bags for easy handling and storage.

Firebond Concentrate (bonding agent) must be applied to all surfaces before application of Z-3306.

Z-3306 is mixed with water in a plaster-type mixer to form a consistent, pumpable slurry. This slurry is then spray applied.

Where desired, the natural sprayed texture of Z-3306 can be lightly trowelled to form a semi-smooth, paintable surface. A thin (nominal ½6 in.) latex stucco overspray may be applied to form a hard eggshell finish, capable of withstanding significant physical contact and surface abrasion.

## **Typical Applications\***

Z-3306 may be used to protect foam plastics in many types of buildings. The following is a brief list of typical applications:

- Breweries, freezers and coolers
- Controlled atmosphere apple, potato and vegetable storage
- Ice arenas and recreation centers
- Indoor tennis courts and swimming pools
- · Pig and dairy barns
- Seed storage and processing
- Water treatment plants
- \* **NOTE:** Many food processing applications require local inspection agency approvals in advance of installation.

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Retro-Guard, Monokote and Spatterkote are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA

In Canada, GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

Printed in U.S.A. TB-106P 12-2016

